



## High Resistance Floor Varnish

- Resistant to heel impact and wear and tear
- High resistance – 60% the hardness of glass
- Stain and water resistant
- 2 coats in one day
- Low odour
- Endorsed by the Guild of Master Craftsmen

<b>USAGE</b>  Interior	<b>COVERAGE</b> 750 ml  10-12 m <sup>2</sup>	<b>APPLICATION</b>  Brush or roller	<b>DRYING TIME</b> 6 hours between coats 24 final	<b>TOOL CLEANING</b>  White Spirit
------------------------------	---	---	---	--

### Product use

Liberon High Resistance Varnish provides exceptional protection for wood floors and a superior resistance to high foot traffic. It is particularly suited to rooms that are in constant use such as hallways, dining rooms, lounges and stairs. High Resistance Varnish offers a durable, high quality finish within 24 hours. It's low odour formula and non-slip finish make it ideal for use in the family home.

### Preparation

Sand the floor if required and remove all previous finishes. Ensure the surface is clean, dry and dust free. If you want to colour the wood you can apply Liberon Wood Floor Dye to the timber before varnishing. Liberon Wood Floor Dye is available in a range of wood shades.

### Application

Stir well before use. Apply High Resistance Varnish evenly with a brush or short hair roller. Allow to dry for a minimum of 6 hours before applying further coats, lightly sanding the surface between coats if required. We recommend a minimum of 3 coats are applied. More coats can be applied for a more durable finish or where foot traffic is particularly heavy. Allow the final coat of varnish a minimum of 24 hours drying time before using the floor.

**Important:** Always test product on a spare surface or inconspicuous area for colour compatibility and end result. A wet surface will be an indication of the final colour.

### Cleaning and maintenance

Wipe any spills immediately. For general maintenance wipe over with a damp mop or cloth using a mild detergent if required. If the surface shows signs of wear re-apply a coat of varnish or coat with Liberon Wood Floor Reviver.

### Precautions

- Allow all wood dyes to dry for a minimum of 8 hours before applying High Resistance Varnish.
- The varnish may raise the grain on some hard woods and may darken some types of timber.
- To reduce the darkening of timber when using Liberon High Resistance Floor Varnish we recommend the use of Liberon Pre-varnish for wood floors.

### VOC Information

EU limit value for High Resistance Varnish (Cat A/I): 600 g/L (2007). High Resistance Varnish contains Max 538 g/L VOC.

### Liberon advice

Apply varnish plank by plank while facing the sunlight. Start in the corner of the room and work back towards the door. Ideal application conditions are between 12 and 25°C.

**Packaging**

2.5 L

**Finishes**

Clear Matt, Clear Satin and Wax Effect

For further information on this or other Liberon products please contact Liberon Technical Services on 01797 361136.

This document was created with Win2PDF available at <http://www.daneprairie.com>.  
The unregistered version of Win2PDF is for evaluation or non-commercial use only.